

Title:

CLASSIFICATION OF REACTION TO FIRE
PERFORMANCE
IN ACCORDANCE WITH
EN 13501-1: 2018.

Product Name:

"Metamark Self Adhesive Vinyl Film"

Report No:

505805

Issue No:

1

Prepared for:

Metamark (UK) Limited
Luneside
New Quay Road
Lancaster
Lancashire
LA1 5QP
United Kingdom

Date:

18th May 2023

1. Introduction

This classification report defines the classification assigned to “Metamark Self Adhesive Vinyl Film”, a family of self-adhesive film products, in line with the procedures given in EN 13501-1: 2018.

2. Details of classified product

2.1 General

The products, “Metamark Self Adhesive Vinyl Film”, are defined as being suitable for construction applications, excluding flooring and linear pipe thermal insulation.

2.2 Product description

The products, “Metamark Self Adhesive Vinyl Film”, are fully described below and in the test reports provided in support of classification listed in Clause 3.1.

Item	Description
General description	A polyvinyl chloride (PVC) film adhered to plasterboard substrate
Family reference	“Metamark Self Adhesive Vinyl Film”
Individual product references	“M7 Series, MD5 Series, MD3 Series, MDi Series, MT Series, MG700 Series, MG300 Series, MGi Series, M4 Series, MD80 Series, MG80 Series, MD100 Series, MG100 Series, MDP Series”
Name of manufacturer	Metamark UK
Thickness of overall composite including substrate	12.41mm (measured by Warringtonfire)
Weight per unit area of overall composite including substrate	10.91kg/m ² (determined by Warringtonfire)

Continued on next page

Item		Description
Test face	General description	Polyvinyl chloride (PVC)
	Component reference	"Self Adhesive Vinyl Film"
	Specific thickness references	"70mic – Solvent Acrylic" and "100mic – Solvent Acrylic"
	Detailed description	See Note 1 below
	Name of manufacturer	See Note 1 below
	Thickness	Between 70 and 80 microns (all colours) 100 microns (White only)
	Weight per unit area	105g/m ²
	Colour	Black, White and Red in matt or gloss finish as
	Flame retardant details	See Note 2 below
Adhesive	General description	100% Solvent based acrylic or Solvent free acrylic based
	Product reference	See Note 1 below
	Detailed description	See Note 1 below
	Name of manufacturer	See Note 1 below
	Thickness	20 microns
	Weight per unit area	See Note 1 below
	Colour reference	See Note 1 below
	Colour	Clear
	Flame retardant details	See Note 2 below
Mounting and fixing details		The specimens were tested applied to a 12.5mm thick paper faced plasterboard substrate as per EN 13238: 2010 as described below.

Item		Description
Substrate	General description	Paper faced plasterboard
	Product reference	"Paper Faced Plasterboard"
	Name of manufacturer	Gyproc
	Thickness	12.5mm
	Density	800kg/m ³
	Flame retardant details	See Note 3 below
Brief description of manufacturing process		Transfer coating on reel to reel basis

Note 1: The sponsor was unwilling to provide this information.

Note 2: The sponsor of the test has confirmed that no flame retardant additives were utilised in the production of the component.

Note 3: The sponsor was unable to provide this information.

3. Test reports/extended application reports & test results in support of classification

3.1 Test reports/extended application reports

Name of Laboratory	Name of sponsor	Test reports/extended application report Nos.	Test method / extended application rules & date
Warringtonfire	Metamark (UK) Limited	Formal: 518694 (Issue 2) Indicative: 508317 (Issue 4), 515448 (Issue 2), 515450 (Issue 2), 515452 (Issue 2), 515453 (Issue 2), 515455 (Issue 2), 515451 (Issue 2), 515449 (Issue 2), 515454 (Issue 2)	EN ISO 11925-2: 2020
Warringtonfire	Metamark (UK) Limited	Formal: 518693 (Issue 2) Indicative: 508315 (Issue 4), 515440 (Issue 2), 515441 (Issue 2), 515442 (Issue 2), 515443 (Issue 2), 515444 (Issue 2), 515445 (Issue 2), 515446 (Issue 2), 515447 (Issue 2)	EN 13823: 2020
Warringtonfire	Metamark (UK) Limited	505804	EN 15725:2010 and EN/TS 15117:2005

3.2 Test results

Test method & test number	Parameter	No. tests	Report	Results	
				Continuous parameter - mean (m)	Compliance parameters
EN ISO 11925-2 (30s exposure - surface)	F _s	6	518694 (12)	-	Compliant (≤ 40 mm)
		1	508317 (14)	-	Compliant (Nil mm)
		1	515448 (12)	-	Compliant (≤ 40 mm)
		1	515450 (12)	-	Compliant (Nil mm)
		1	515452 (12)	-	Compliant (≤ 30 mm)
		1	515453 (12)	-	Compliant (≤ 30 mm)
		1	515455 (12)	-	Compliant (≤ 30 mm)
		1	515451 (12)	-	Compliant (Nil mm)
		1	515449 (12)	-	Compliant (Nil mm)
		1	515454 (12)	-	Compliant (≤ 30 mm)
	Flaming droplets/ particles	6	518694 (12)	-	Compliant
		1	508317 (14)	-	Compliant
		1	515448 (12)	-	Compliant
		1	515450 (12)	-	Compliant
		1	515452 (12)	-	Compliant
		1	515453 (12)	-	Compliant
		1	515455 (12)	-	Compliant
		1	515451 (12)	-	Compliant
		1	515449 (12)	-	Compliant
		1	515454 (12)	-	Compliant

Continued on next page

EN ISO 11925-2 (30s exposure - edge)	F _s	6	518694 (12)	-	Compliant (≤ 30 mm)
		1	508317 (14)	-	Compliant (≤ 30 mm)
		1	515448 (12)	-	Compliant (≤ 20 mm)
		1	515450 (12)	-	Compliant (≤ 20 mm)
		1	515452 (12)	-	Compliant (≤ 20 mm)
		1	515453 (12)	-	Compliant (≤ 30 mm)
		1	515455 (12)	-	Compliant (≤ 20 mm)
		1	515451 (12)	-	Compliant (≤ 30 mm)
		1	515449 (12)	-	Compliant (≤ 30 mm)
		1	515454 (12)	-	Compliant (≤ 20 mm)
	Flaming droplets/ particles	6	518694 (12)	-	Compliant
		1	508317 (14)	-	Compliant
		1	515448 (12)	-	Compliant
		1	515450 (12)	-	Compliant
		1	515452 (12)	-	Compliant
		1	515453 (12)	-	Compliant
		1	515455 (12)	-	Compliant
		1	515451 (12)	-	Compliant
		1	515449 (12)	-	Compliant
1		515454 (12)	-	Compliant	
EN 13823	FIGRA _{0.2MJ}	3	518693 (12)	116 W/s	-
		1	508315 (14)	66 W/s	-
		1	515440 (12)	127 W/s	-
		1	515441 (12)	90 W/s	-
		1	515442 (12)	108 W/s	-
		1	515443 (12)	66 W/s	-
		1	515444 (12)	94 W/s	-
		1	515445 (12)	41 W/s	-
		1	515446 (12)	115 W/s	-
		1	515447 (12)	63 W/s	-

Continued on next page

EN 13823	FIGRA _{0.4MJ}	3	518693 (12)	48 W/s	-
		1	508315 (14)	25 W/s	-
		1	515440 (12)	0 W/s	-
		1	515441 (12)	8 W/s	-
		1	515442 (12)	0 W/s	-
		1	515443 (12)	0 W/s	-
		1	515444 (12)	32 W/s	-
		1	515445 (12)	24 W/s	-
		1	515446 (12)	32 W/s	-
		1	515447 (12)	9 W/s	-
	THR _{600s}	3	518693 (12)	1.0 MJ	-
		1	508315 (14)	0.9 MJ	-
		1	515440 (12)	0.7 MJ	-
		1	515441 (12)	1.5 MJ	-
		1	515442 (12)	0.5 MJ	-
		1	515443 (12)	0.5 MJ	-
		1	515444 (12)	1.8 MJ	-
		1	515445 (12)	1.3 MJ	-
		1	515446 (12)	1.0 MJ	-
		1	515447 (12)	0.4 MJ	-
	LFS	3	518693 (12)	-	Compliant
		1	508315 (14)	-	Compliant
		1	515440 (12)	-	Compliant
		1	515441 (12)	-	Compliant
		1	515442 (12)	-	Compliant
		1	515443 (12)	-	Compliant
		1	515444 (12)	-	Compliant
		1	515445 (12)	-	Compliant
		1	515446 (12)	-	Compliant
		1	515447 (12)	-	Compliant
	SMOGRA	3	518693 (12)	4 m ² /s ²	-
		1	508315 (14)	14 m ² /s ²	-
		1	515440 (12)	0 m ² /s ²	-
		1	515441 (12)	0 m ² /s ²	-
		1	515442 (12)	15 m ² /s ²	-
		1	515443 (12)	10 m ² /s ²	-
		1	515444 (12)	0 m ² /s ²	-
		1	515445 (12)	0 m ² /s ²	-
		1	515446 (12)	27 m ² /s ²	-
		1	515447 (12)	18 m ² /s ²	-

- Continued on next page

EN 13823 continued	TSP _{600s}	3	518693 (12)	29 m ²	-
		1	508315 (14)	51 m ²	-
		1	515440 (12)	22 m ²	
		1	515441 (12)	34 m ²	-
		1	515442 (12)	49 m ²	-
		1	515443 (12)	45 m ²	-
		1	515444 (12)	23 m ²	-
		1	515445 (12)	34 m ²	-
		1	515446 (12)	47 m ²	-
		1	515447 (12)	55 m ²	-
	Fall of Flaming Droplet/Particle?	3	518693 (12)	-	Compliant
		1	508315 (14)	-	Compliant
		1	515440 (12)	-	Complaint
		1	515441 (12)	-	Compliant
		1	515442 (12)	-	Compliant
		1	515443 (12)	-	Compliant
		1	515444 (12)	-	Compliant
		1	515445 (12)	-	Compliant
		1	515446 (12)	-	Compliant
		1	515447 (12)	-	Compliant
	Flaming of Fallen Particle Exceeding 10s?	3	518693 (12)	-	Compliant
		1	508315 (14)	-	Compliant
		1	515440 (12)	-	
		1	515441 (12)	-	Compliant
		1	515442 (12)	-	Compliant
		1	515443 (12)	-	Compliant
		1	515444 (12)	-	Compliant
		1	515445 (12)	-	Compliant
		1	515446 (12)	-	Compliant
		1	515447 (12)	-	Compliant

4. Classification and field of application

4.1 Reference of classification

This classification has been carried out in accordance with clause 8 of EN 13501-1: 2018, EN 15725:2010 and EN/TS 15117:2005.

4.2 Classification

The products, "Metamark Self Adhesive Vinyl Film", a family of self-adhesive film products, in relation to their reaction to fire behaviour are classified:

B

The additional classification in relation to smoke production is:

s2

The additional classification in relation to flaming droplets / particles is:

d0

The format of the reaction to fire classification for construction applications, excluding flooring and linear pipe thermal insulation is:

Fire Behaviour		Smoke Production			Flaming Droplets	
B	-	s	2	,	d	0

i.e. **B – s2 , d0**

Reaction to fire classification: B – s2, d0

4.3 Field of application

This classification is valid for the following end use applications:

- i) Construction applications applied to any substrate with a density equal to or greater than 525kg/m^3 , having a minimum thickness of 12mm and a fire performance of A2-s1, d0 or better.
- ii) Product installed utilising inherent self-adhesive backing of solvent based acrylic or solvent free acrylic as described, at an application thickness of 20 microns.

This classification is also valid for the following product parameters:

Product thickness	70 microns for all colours and between 70 and 100 microns for white colour only.
Product weight per unit area	No variation allowed
Product colour	All colours for 70 microns and white only for 100 microns
Product composition	No variation allowed
Adhesive backing	Solvent based acrylic adhesive or solvent free acrylic adhesive
Product construction	No variation allowed
Joints	No joints allowed

5. Limitations

This document does not represent type approval or certification of the product.

SIGNED

APPROVED



.....
Claire Lawrence
Product Assessor
Technical Department

.....
Stacey Deeming
Principal Product Assessor
Technical Department
on behalf of [Warringtonfire](#)

This copy has been produced from a .pdf format electronic file that has been provided by **Warringtonfire** to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of **Warringtonfire**. The pdf copy supplied is the sole authentic version of this document. All pdf versions of this report bear authentic signatures of the responsible **Warringtonfire** staff.

All work and services carried out by Warringtonfire Testing and Certification Limited are subject to, and conducted in accordance with, the Standard Terms and Conditions of Warringtonfire Testing and Certification Limited, which are available at <https://www.element.com/terms/terms-and-conditions> or upon request.